



# KF MODULE Polycrystalline

#### KF-P80W

- $\boldsymbol{\ast}$  High transmittance, low iron tempered glass with enhanced stiffness and impact resistance.
- \* Unique frame design with high mechanical strength for easy installation.
- \* Advanced encapsulation material with multilayer sheet lamination to provide long-life and enhanced cell performance.
- \* Outstanding electrical performance under high temperature and low irradiance conditions.
- \* Carbon Friendly.

#### Warranty:

5 years for product defects in materials and workmanship 10 years for 90% of warranted minimum power

25 years for 80% of warranted minimum power

#### Certificates:






IEC: IEC 61215, IEC 61730 (1&2), conformity to CE

ISO9001:2008 GB/T 19001-2008

ISO9001:2008 Quality Management System

 $\label{eq:pv} \mbox{PV Cycle: Voluntary module take back and recycling program}$ 





### KF-P80W

Specification for Poly-Crystalline Silicon Solar2 Module with 80W Maximum Power

## SPECIFICATION DATA

| Cell                          | Poly-Crystalline silicon solar cells |
|-------------------------------|--------------------------------------|
| No. of cells and connections  | 72series                             |
| Application                   | DC 12V system                        |
| Max. system voltage           | 715VDC                               |
| Power tolerance               | ±3%                                  |
| Surface Maximum Load Capacity | 60 m/s(200kg/sq. m)                  |
| Weight                        | 8.0kg                                |
| Dimensions                    | 990*670*35mm                         |
| Packing                       | 6pcs/ctn                             |

## **ELECTRICAL CHARACTERISTICS**

| Max. power                         | 80W                    |
|------------------------------------|------------------------|
| Open circuit voltage(V)            | 21.5                   |
| Short circuit cyrrent(A)           | 5.17                   |
| Max. power voltage(V)              | 17.5                   |
| Max. power cyrrent(A)              | 4.57                   |
| Temperature coefficients of Isc(%) | 0.1/°C                 |
| Temperature coefficients of Voc(%) | -0.33/°C               |
| Temperature coefficients of Pm(%)  | -0.23/°C               |
| Temperature coefficients of Im(%)  | 0.08/°C                |
| Temperature coefficients of Vm(%)  | -0.33/°C               |
| Cells Efficiency(%)                | ≥14.5                  |
| FF(%)                              | 73                     |
| Conditions: (STD)                  | Irradiance: 1000W/m²   |
|                                    | Cell temperature: 25°C |

# ABSOLUTE MAXIMUM RATING

| Operating temperature | -40~ +80°C |
|-----------------------|------------|
| Storage temperature   | -40~ +80°C |