

## Technical Data

## PHOTOCAP<sup>®</sup> FC295P

PHOTOCAP<sup>®</sup> FC295P is a fast cure EVA (ethylene vinyl acetate copolymer) photovoltaic encapsulating film material. PHOTOCAP FC295P improved photo-thermal stability relative to PHOTOCAP 15295P.

PHOTOCAP FC295P can be used for all crystalline silicon photovoltaic module constructions, and for many thin film photovoltaic designs. PHOTOCAP FC295P is provided as rolled film ready for use in thermal lamination processes. The material is self-priming for adhesion to glass.

Properties	Test Method ASTM	Units	Condition	Results
<b>Physical Mechanical</b>				
Tensile Strength	D638	MPa	23 °C, 250 mm/min elongation rate	18.1
Ultimate Elongation	D638	%	23 °C, 250 mm/min elongation rate	700
10% Secant Modulus	D638	MPa	23 °C, 250 mm/min elongation rate	7.8
Hardness	D2240	Shore A/D	23 °C	69 / 21
Adhesion to Glass	STR	N/cm	23 °C	70-90
MVTR	F1249	g/m <sup>2</sup> /day	25 °C/100sccm flow, 100%RH	23
Water Absorption	D570	wt%	23 °C	< 0.1
<b>Optical</b>				
Optical Transmission	E424	%	23 °C, 0.46 mm thickness	92
UV Cutoff Wavelength	E424	nm	23 °C, 0.46 mm thickness	360
Refractive Index	D542	-	23 °C, 0.46 mm thickness	1.482
<b>Electrical</b>				
Volume Resistivity	D257	ohm cm	23 °C	>1 x 10 <sup>14</sup>
Dielectric Strength	D149	kV/mm	23 °C, 500V/sec	24

Tests are made in accordance with the current issue of the ASTM, or other cited test method. Test data reported here are nominal values measured on extruded films, 0.5 mm thick, or compression molded sheets and test bars, which have been cured at 150 °C for 7 minutes with a laboratory press. Optical measurements made with glass-EVA coupons with high transmission solar glass.

### Americas

Specialized Technology Resources, Inc.  
 18 Craftsman Road  
 East Windsor, CT 06088  
 USA  
 Phone: +1 860 763 7014  
 Email: [sales@STRSolar.com](mailto:sales@STRSolar.com)

### Europe

Specialized Technology Resources, España  
 Parque Tecnológico de Asturias,  
 parcela 36  
 33428 Llanera, Asturias  
 SPAIN  
 Phone: +34 985 73 23 33  
 Email: [sales@STRsolar.com](mailto:sales@STRsolar.com)

### Asia

Specialized Technology Resources, Malaysia  
 Plot 20, Jalan Tanjung A/3  
 Port of Tanjung Pelepas  
 81560 – Gelang Patah, Johor  
 MALAYSIA  
 Phone: +607 507 3185  
 Email: [sales@STRSolar.com](mailto:sales@STRSolar.com)

**Technical Data**  
page 2

**PHOTOCAP<sup>®</sup> FC295P**

**AGENCY APPROVALS:**

PHOTOCAP FC295P is a UL listed product in category QIHE2 Photovoltaic Polymeric Materials. Each STR manufacturing plant maintains a separate UL file. Please refer to UL file numbers E349543, E335471 and E335472.

**PRODUCT VARIATIONS:**

Suffix	Release Paper	Shrinkage	Notes
FC295P/UF	Yes	Zero	STR's User Friendly (UF) technology allows sheets to be cut closer to size, resulting in less voids and shifting of ribbon and cells
FC295P/UEP	No	Minimal	Paperless UF option, resulting in minimal shrinkage
FC295P/PL	No	Higher than UF or UEP	Possesses a greater tendency to shrink but perfectly acceptable for use

**PROCESS GUIDELINES:**

Vacuum Lamination Step		Heat Cure Cycle	
Nominal Temperature	145 - 150 °C	Platen Temperature	145 - 150 °C
Vacuum Range	< 60 mbar	Cure Time	12 min
Evacuation Time	4 min	Applied Bladder Pressure	910 mbar
EVA Melting Range Via DSC	60 - 70 °C	Target Temperature within the Encapsulant	140 °C
		Time Above the Target Temperature	> 6 min

*Processing conditions shown here are a recommended starting point for a crystalline silicon photovoltaic module processed with a typical 2-step vacuum lamination system. Actual values required to achieve desired cure levels will depend on the specific PV module design and the lamination process used.*

*The temperature of the encapsulant should be at or above the EVA melting range before pressure is applied for the cure cycle. The encapsulant should reach the target temperature during the cure cycle, and should remain above that target temperature for the time shown. Temperatures within encapsulant should be periodically measured with embedded thermocouples to assess temperature uniformity of the laminator heating plate and the rate of heat transfer to the PV module. More information about how to laminate PV modules with PHOTOCAP encapsulants is available from STR.*

All PHOTOCAP grades are based upon over 30 years of STR's commercial experience in the photovoltaic market.

For further information, please contact the nearest Specialized Technology Resources office or agent.

PHOTOCAP<sup>®</sup> is a registered trademark of Specialized Technology Resources, Inc. The data set forth above is believed to be accurate. It is for informational purposes only and is not to be used for specification purposes. Neither Specialized Technology Resources, Inc., nor any of its affiliates, makes any representation or warranty as to, and disclaims all liability for, the information herein. PHOTOCAP is to be used by technically skilled persons at their own discretion and risk.