

Product Data Sheet
VISTASOLAR® EVA Encapsulant
Type: 496 – Fast Cure – Transparent



SOLUTIA SOLAR GMBH
A subsidiary of Eastman Chemical
Industriestr. 3
D-89165 Dietenheim Germany
Telephone: +49 (0) 7347 9223-0

Technical Properties	Test method	Unit	Uncured	Cured
Density	ISO 1183-3	g/cm ³	0.95	0.96
Tensile strength	MD	N/mm ³	6-7	20-25 ⁽¹⁾
	TD		6-7	20-25 ⁽¹⁾
Elongation at break	MD	%	> 1,000	> 500 - 700 ⁽¹⁾
	TD		> 1,000	> 500 - 700 ⁽¹⁾
Secant modulus at 1% elongation	ISO 527-3	N/mm ³	5-6	10-14 ⁽¹⁾
Shrinkage on glass (120°C/5 min)	Solutia Internal	MD%	--	< 5
		TD%	--	< 5
Hardness shore A	DIN 53 505	--	--	68-72 ⁽¹⁾
Thermal elongation at temperature	ISO 11359-2			
< -43°C (glass transition)		K ⁻¹	1.0 x 10 ⁻⁴	.90 x 10 ⁻⁴
-43 bis -20°C		K ⁻¹	2.0 x 10 ⁻⁴	2.0 x 10 ⁻⁴
-19 bis +10°C		K ⁻¹	6.0 x 10 ⁻⁴	2.0 x 10 ⁻⁴
> 10°C		K ⁻¹	15.0 x 10 ⁻⁴	4.0 x 10 ⁻⁴
Optical reflection (390–1105 nm)	Solutia Internal	%	--	8-9
Optical transmission (390–1105 nm)	Solutia Internal	%	--	> 92
UV Cut off	Solutia Internal	nm	--	360
Refractive index	ATM D542	--	--	1.479
VISTASOLAR 496.00	Surface	Structured non-sticky (one side)		
VISTASOLAR 496.10		Structured non-sticky (both sides)		

This technical information is intended as a guideline only.

Notice: Although the information and/or recommendations as may be set forth herein (hereafter "Information") are presented in good faith and believed to be correct at the date hereof, Solutia Inc. and its affiliates (hereinafter "Solutia") make no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Solutia be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent and Solutia makes no representation or warranty, express or implied, that the use thereof will not infringe any patent.

NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

© 2012 Solutia Inc. All rights reserved. Saflex®, VISTASOLAR®, Solutia and Radiance Logo™ are trademarks of Solutia Inc., a subsidiary of the Eastman Chemical Company. As used herein, ® denotes registered status in the U.S. only.